


# Excel Enbeam Single Internal 5/3.5 mm Blowing Tube LSOH White

excel  
without compromise.

Part Code: 208-770

sales@excel-networking.com  
excel-networking.com



## Main Features

- / Internal application
- / Multiple sizes available
- / Crush and impact resistant
- / LSOH sheath
- / Multiple bundle configurations
- / RoHS compliant

## Product Overview

Enbeam Internal blowing tubes have been designed to allow blown fibre to be distributed internally. The internal grade tubes are over-sheathed with Polyethylene and Halogen free (HF) flame retardant material. All internal tubes are colour coded for easy identification and have a low friction inner coating to reduce drag & maximise blowing distances.

Tubes are easily broken out of the main sheath and can be branched-off using the Enbeam push-fit blown tube connectors. The tubes are supplied on disposable wooden drums and capped at both ends to prevent ingress of moisture or contamination.

# Excel Enbeam Single Internal 5/3.5 mm Blowing Tube LS0H White

Part Code: 208-770

sales@excel-networking.com  
excel-networking.com

## Product Specifications

Feature	Values
Halogen free	yes
Outer sheath colour	White

## Additional specifications

Features	Values
Sheath material	LSZH
Pressure	<b>Burst</b> min. 50 bar
	<b>Blowing</b> 16 bar (recommended)
Recommended cable diameter	1.1-2.5mm

## Additional specifications

Features	Values
Outer diameter (OD)	5±0.1mm
Inner diameter (ID)	min. 3,4mm
Ovality	max. 5%
Sheath thickness (mm)	1.5
Installation tensile force, max	100 N
Min. bending radius (mm)	50
Weight (kg/km)	10
Operating temperatures	-40°C to 70°C

# Excel Enbeam Single Internal 5/3.5 mm Blowing Tube LS0H White

Part Code: 208-770

sales@excel-networking.com  
excel-networking.com

Transport/storage temperatures **-10°C to 50°C**

Installation temperatures **-40°C to 70°C**

## Standards

Applicable standard	Detail
EN ISO 291:2008	Plastics – Standard atmospheres for conditioning and testing
EN ISO 2505:2005	Thermoplastics pipes – Longitudinal reversion – Test method
ČSN 010254:1976	Sampling inspection by attributes
EN ISO 1167-1:2006	Thermoplastics pipes, fittings and assemblies for the conveyance of fluids – Determination of the resistance to internal pressure
EN 12201-1:2011	Plastics piping systems for water supply, and for drainage and sewerage under pressure – PE
EN 12201-2:2011+A1:2013	Plastics piping systems for water supply, and for drainage and sewerage under pressure – Polyethylene (PE) – Part 2: Pipes
EN ISO 3127:2017	Plastics piping and ducting systems – Thermoplastics pipes – Test method for resistance to external blows by the round-the-clock method
IEC 60 794-1-1:2015	Optical fibre cables – Part 1-1: Generic specification – General
IEC 60 794-1-2:2017	Optical fibre cables – Part 1-2: Generic specification – Basic optical cable test procedures – General guidance
IEC 60794-1-21:2015+AMD1:2020	Optical fibre cables – Part 1-21: Generic specification – Basic optical cable test procedures – Mechanical tests methods
IEC 60 794-1-22:2017	Optical fibre cables – Part 1-22: Generic specification – Basic optical cable test procedures – Environmental tests

# Excel Enbeam Single Internal 5/3.5 mm Blowing Tube LS0H White

Part Code: 208-770

sales@excel-networking.com  
excel-networking.com

	methods
IEC 60 794-1-23:2019	Optical fibre cables – Part 1-23: Generic specification – Basic optical cable test procedures – Cable element test methods
EN IEC 60 794-1-24:2014	Optical fibre cables – Part 1-24: Generic specification – Basic optical cable test procedures – Electrical test methods
IEC 60 794-2:2017	Optical fibre cables – Part 2: Indoor cables – Sectional specification
ASTM D 1894-14	Standard Test Method for Static and Kinetic Coefficient of Friction of Plastic Film and Sheeting
ASTM D2122-16	Standard Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
EN 13501-1:2018	Fire classification of construction products and building elements – Part 1: Classification using data from reaction to fire tests
ISO 6259-1,2,3:1997-2015	Thermoplastic pipes – Determination of tensile properties
ISO 3126:2005	Plastics piping systems – Plastics components – Determination of dimensions
ISO 527-1:2019	Plastics – determination of tensile properties – Part 1: General principles
ISO 1133-1:2011	Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics
EN 61386-24:2010	Conduit systems for cable management – Part 24: Particular requirements – Conduit systems buried underground.
ISO 1183-1:2019	Plastics – Methods for determining the density of non-cellular plastics – Part 1: Immersion method, liquid pycnometer method and titration method
ISO 1183-2:2019	Part 2: Density gradient column method
ISO 6964:2019	Polyolefin pipes and fittings – Determination of carbon black content by calcination and pyrolysis – Test method
ISO 18553:2002+Amd 1:2007	Method for the assessment of the degree of pigment or carbon black dispersion in polyolefin pipes, fittings and

# Excel Enbeam Single Internal 5/3.5 mm Blowing Tube LS0H White

Part Code: 208-770

sales@excel-networking.com  
excel-networking.com

	compounds
ISO 9969:2016	Thermoplastics pipes – Determination of ring stiffness
EN ISO 13263:2017	Thermoplastics piping systems for non-pressure underground drainage and sewerage – Thermoplastics fittings – Test method for impact strength
IEC 60304:1982	Color code
ASTM D 1693:2015	Standard Test Method for Environmental Stress Cracking of Ethylene Plastics
ISO 11357-6:2018	Plastics – Differential scanning calorimetry (DSC) – Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)
ČSN EN ISO 899-2:2003/A1:2015	Plastics – Determination of creep behavior – Part 2: Flexural creep by three-point loading – Amendment 1
IEC 60 794-3-20:2016	Optical fibre cables – Part 3-20: Outdoor cables – Family specification for self-supporting aerial telecommunication cables
IEC 60794-4:2018	Optical fibre cables – Part 4: Sectional specification – Aerial optical cables along electrical power lines
IEC 60 794-5:2014	Optical fibre cables – Sectional specification – Microduct cabling for installation by blowing
Directive 2011/65/EU (RoHS II)	Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment — compliant. Applies within EU member states).
Directive (EU) 2015/863 (RoHS III)	Amending Directive 2011/65/EU to add four phthalates (DEHP, BBP, DBP, DIBP) to Annex II — compliant.
Directive 2008/98/EC (WFD)	Waste Framework Directive — compliant. Implemented in the UK through the Waste (England and Wales) Regulations 2011 (SI 2011 No. 988).
ECHA SCIP Database	Compliant; product does not contain SVHCs (Substances of Very High Concern) as defined under REACH Article 33(1). Submission obligations met under EU REACH and UK REACH.
Regulation (EU) 2019/1021 (POPs)	EU Regulation on Persistent Organic Pollutants — compliant. For Great Britain, compliance is aligned with the Persistent Organic Pollutants (Amendment) (EU Exit)

# Excel Enbeam Single Internal 5/3.5 mm Blowing Tube LS0H White

Part Code: 208-770

sales@excel-networking.com  
excel-networking.com

Regulations 2020 (SI 2020 No. 1355).

UK SI 2012 No. 3032

The Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment Regulations 2012 (UK RoHS) — compliant for Great Britain. Retained EU law, as amended by the Product Safety and Metrology (Amendment etc.) (EU Exit) Regulations 2019.

## Part Code Table

Part Code	Description
208-770	<b>Excel Enbeam Single Internal 5/3.5 mm Blowing Tube LS0H White</b>