

✗ G.657.A1 bend insensitive

✗ Available in 4, 8 & 12-fibre bundles

✗ TIA-598-C colour coded

✗ Gel free dielectric design

✗ Coated for improving blowing performance

✗ 25 year system warranty

## Product Overview

Enbeam OS2 singlemode G.657.A1 blown fibre EPFU 4 fibre 9/125 yellow, part of a huge range of OS2 fibre optic cables fully stocked at Mayflex.

Enbeam Enhanced Performance Fibre Units (EPFU) are designed specifically for blown-fibre applications and are optimised for installation within our range of blown-fibre tubes.


The fibres are contained within a soft acrylate layer which cushions the fibres. This layer is coated with a hard layer for strength and finally a low-friction coating to ensure low drag and maximise blowing distances within the tubes.

The acrylate coatings are easy to remove to expose the 250-micron primary-coated fibres for quick splicing. The fibres are colour-coded according to TIA-598-C.


## Product Specifications

Feature	Values
Number of Cores	4
Fibre type	Single mode 9/125
Category	OS2
Outer sheath colour	Yellow
Outer diameter approx.	1.15 mm
Blown system	yes


### Product drawing



**4**  
Fibre Units



**8**  
Fibre Units



**12**  
Fibre Units

### Cable specifications

Features		Values
Weight (kg/km)	4 Fibres	$1.0 \pm 0.3$
	8 Fibres	$1.8 \pm 0.3$
	12 Fibres	$3.0 \pm 0.3$
Tensile performance (N)	Short term	1*G
	Long term	0.3*G
Crush (N/100 mm)	Short term	100
	Long term	50

Blowing test equipment	PLUMETTAZ: UltimaZ™	
Standard duct	5.0/3.5 mm	
Pressure	12 bar	
Typical blowing distance	4 Fibres	1000 m
	8 Fibres	1000 m
	12 Fibres	800 m
Typical blowing time	4 Fibres	35 min
	8 Fibres	35 min
	12 Fibres	30 min
Temperature	Transportation and storage	-40°C to +70°C
	Installation	-5°C to +50°C
	Operation	-20°C to +70°C

## Fibre specifications

Features	Values
Attenuation (before cabling)	≤ 0.35 dB/km @ 1310 nm
	≤ 0.21 dB/km @ 1550 nm
Attenuation (after cabling)	≤ 0.36 dB/km @ 1310 nm
	≤ 0.25 dB/km @ 1550 nm
Attenuation change over wavelength range	≤ 0.38 dB/km 1285 nm - 1330 nm
	≤ 0.25 dB/km 1525 nm - 1575 nm
	≤ 0.28 dB/km 1460 nm - 1625 nm
Chromatic Dispersion Coefficient	≤ 3.5 ps/km·nm 1288 nm - 1339 nm
	≤ 5.3 ps/km·nm 1271nm - 1360 nm
	≤ 18.0 ps/km·nm @ 1550 nm
Zero Dispersion Wavelength, $\lambda_0$	1300 - 1324 nm
Zero Dispersion Slope	≤ 0.092 ps/(km·nm <sup>2</sup> )
Cut-off Wavelength, $\lambda_{cc}$	≤ 1260 nm
Macro Bending Loss	≤ 0.25 dB @ 1550 nm 10 turns, 15 mm radius
	≤ 1 dB @ 1625 nm
	≤ 0.75 dB @ 1550 nm 1 turn, 10 mm radius

		$\leq 1.50 \text{ dB} @ 1625 \text{ nm}$
Cladding Diameter		$125.0 \pm 0.7 \mu\text{m}$
Cladding Non-circularity		$\leq 0.7\%$
Coating Non-circularity		$\leq 5\%$
Coating Diameter		$250 \pm 10 \mu\text{m}$
Core - Cladding Concentricity Error		$\leq 0.5 \mu\text{m}$
Coating - Cladding Concentricity Error		$\leq 12 \mu\text{m}$
Fibre Curl Radius		$\geq 4 \text{ m}$
Mode Field Diameter	@ 1310 nm	$9.1 \pm 0.3 \mu\text{m}$
	@ 1550 nm	$10.3 \pm 0.5 \mu\text{m}$
Point discontinuity		$\leq 0.05 \text{ dB}$
Proof Stress Level		$\geq 0.7 \text{ Gpa} (\approx 1\% \text{ strain})$
Dynamic Tensile Strength	Median	$> 3.8 \text{ GPa}$
Fatigue	Dynamic, aged and unaged	$\geq 20$
	Static, aged	$\geq 23$
Coating strip force	Average	1 N to 3 N
	Peak	$1.3 \leq F \leq 8.9$

### Colour coding (as per TIA-598-C)



### Standards

Applicable standard	Subject
ITU G.652.D	Characteristics of a single-mode optical fibre and cable
ITU-T G.657A1	Characteristics of a bending loss insensitive single-mode optical fiber
ANSI/TIA/EIA 598-C	Optical Fibre Cable Colour Coding

IEC 60794-1-2:2017	Optical fibre cables - Part 1-2: Generic specification - Basic optical cable test procedures - General guidance
IEC 60068-2-38:2009	Environmental testing - Part 2-38: Tests - Test Z/AD: Composite temperature/humidity cyclic test
IEC 60794-5:2014	Optical fibre cables - Part 5: Sectional specification - Microduct cabling for installation by blowing
IEC 60794-5-10:2014	Optical fibre cables - Part 5-10: Family specification - Outdoor microduct optical fibre cables, microducts and protected microducts for installation by blowing
RoHS-II/-III (2011/65/EU & 2015/863): 2023	Our products, demonstrate full adherence to the regulatory stipulations of the EU Directive 2011/65/EU (RoHS-II) and its corresponding delegated directive 2015/863 (RoHS-III).
WFD: 2023	Compliant to Waste Framework Directive
SCIP: 2023	Compliant - Does Not Contain Substances of Concern In articles as such or in complex objects (Products)
POPs (EU) No 2019/1021	EU Regulation for the restriction of Persistent Organic Pollutants.

### Part Number Table

Part Number	Description
208-812	Excel Enbeam OS2 Singlemode G.657.A1 Blown Fibre EPFU 4 Fibre 9/125 Yellow
208-813	Excel Enbeam OS2 Singlemode G.657.A1 Blown Fibre EPFU 8 Fibre 9/125 Yellow
208-814	Excel Enbeam OS2 Singlemode G.657.A1 Blown Fibre EPFU 12 Fibre 9/125 Yellow

Excel is a world class premium performing end to end infrastructure solution designed, Manufactured, supported and delivered without compromise.

Contact us at [sales@excel-networking.com](mailto:sales@excel-networking.com)

E&OE. Excel is a registered trade name of Mayflex Holdings Ltd.

**excel**  
without compromise.